

[Sign in](#)

Patents

Application

Grant

[Find prior art](#)[Discuss this patent](#)[View PDF](#)[Download PDF](#)

Polymerization method and product

US 9296861 B2

ABSTRACT

Methods of preparing a polyaniline homopolymer or copolymer comprising at least one carboxylic acid group, and homopolymers or copolymers arising therefrom, the methods comprising: preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group (eg. 2-aminobenzoic acid, 3-aminobenzoic acid or 4-aminobenzoic acid) in a solvent selected from aqueous methanesulfonic acid or aqueous ammonia and optionally one or more additional polyaniline precursors (such as aniline); and oxidatively polymerising the polyaniline precursor or precursors.

DESCRIPTION

CROSS REFERENCE TO RELATED APPLICATIONS

This application is a national stage application under 35 U.S.C. 371 and claims the benefit of PCT Application No. PCT/NZ2012/000047 having an international filing date of 27 Mar. 2012, which designated the United States, and which PCT application claimed the benefit of New Zealand Patent Application No. 592081 filed on 05 Apr. 2011, the entire disclosure of each is incorporated by reference herein.

TECHNICAL FIELD

The invention relates to processes for preparing polymers that include aminobenzoic acid monomers, and to copolymers and homopolymers prepared by those processes.

BACKGROUND ART

Polymers of aniline and its derivatives are useful as antimicrobial agents and have good antistatic and free radical scavenging properties. These properties make them useful for the manufacture of antimicrobial, antistatic and antioxidant objects, and suitable for use in, for example, the health, food, packaging, water, paint, wood, textile, poultry, glass, paper, rubber, ceramic, seafood, sports, plastic and agricultural industries.

Adding substituents to polyaniline (PANI) is one way in which the various properties of the polymer can be improved. However, the synthesis of substituted PANIs is not always a straightforward matter. Any substituent introduced to the aniline building block needs to be compatible with the reagents used, which is not always possible under the traditionally robust oxidative polymerisation conditions used to form PANIs.

Carboxylated PANIs are one type of PANI derivative of particular interest due to their good antibacterial properties. Carboxylated PANIs can either be homopolymers, which could also be described as a poly(aminobenzoic acid) (poly ABAs) or copolymers, which could be considered as a PANI backbone bearing carboxylic acid groups on some of the aromatic rings. Figure 1 shows the probable structure of poly(2-aminobenzoic acid) and poly(3-aminobenzoic acid). Figure 2 shows the probable structure of copolymers of aniline and 2-

Publication number	US9296861 B2
Publication type	Grant
Application number	US 14/110,052
PCT number	PCT/NZ2012/000047
Publication date	Mar 29, 2016
Filing date	Mar 27, 2012
Priority date	Apr 5, 2011
Also published as	US20140155571 , US20160208048 , WO2012138234A1
Inventors	Sudip Ray , Allan James Easteal
Original Assignee	Auckland Uniservices Limited
Export Citation	BiBTeX , EndNote , RefMan
Patent Citations	(5), Non-Patent Citations (2), Classifications (11), Legal Events (1)
External Links:	USPTO , USPTO Assignment , Espacenet

CLAIMS (11)

The claims defining the invention are as follows:

1. A method of preparing a polyaniline homopolymer or copolymer comprising at least one carboxylic acid group, the method comprising:

preparing an acidic or near neutral (pH 7-8) solution of 15% by weight or higher of a first polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in a solvent selected from the group consisting of aqueous methanesulfonic acid and aqueous ammonia;

wherein the solution optionally includes one or more additional polyaniline precursors; and

oxidatively polymerising the polyaniline precursor an additional precursors, if present.

2. The method of claim 1, further comprising:

preparing the solution of the first polyaniline precursor in aqueous methanesulfonic acid; and

oxidatively polymerising the polyaniline precursor.

3. The method of claim 1, further comprising:

preparing a solution of the first polyaniline precursor in aqueous ammonia; and

oxidatively polymerising the polyaniline precursor.

4. The method of claim 1, further comprising:

preparing the solution of the first polyaniline precursor and the one or more additional polyaniline precursors in aqueous methanesulfonic acid; and

oxidatively polymerising the first polyaniline precursor and the one or more additional polyaniline precursors.

5. The method of claim 1 further comprising:

Try the new Google Patents, with machine-classified Google Scholar results, and Japanese and South Korean patents.

Figure US09296861-20160329-C00001

However, producing PANI homopolymers and copolymers from aminobenzoic acid (ABA) monomers in good yield and purity is not a simple procedure. There are significant problems with the solubilities of ABAs. ABAs tend to be solids, unlike aniline itself or many substituted anilines (alkyl anilines like toluidine, alkoxy anilines like anisidine etc) which can be used directly in their liquid form. This low solubility impacts upon the cost of synthesis and the quality of the resultant polymers.

There thus exists a need to produce poly-ABAs (carboxylated PANIs) in high yield and in a cost effective manner, with high conversion of monomer units, short production time and high molecular weights.

It is an object of the present invention to overcome or ameliorate at least one of the disadvantages of the prior art, or to provide a useful alternative.

SUMMARY

In a broad aspect, the invention provides a method of preparing a polyaniline homopolymer or copolymer comprising at least one carboxylic acid group; the method comprising:

- preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in a solvent selected from aqueous methanesulfonic acid or aqueous ammonia and optionally one or more additional polyaniline precursors; and
- oxidatively polymerising the polyaniline precursor or precursors.

Unless the context clearly requires otherwise, throughout the description and the claims, the words "comprise", "comprising", and the like are to be construed in an inclusive sense as opposed to an exclusive or exhaustive sense; that is to say, in the sense of "including, but not limited to".

In one aspect, the invention provides a method of preparing a polyaniline homopolymer comprising carboxylic acid groups; the method comprising:

- preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in aqueous methanesulfonic acid; and
- oxidatively polymerising the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group.

In one aspect, the invention provides a method of preparing a polyaniline homopolymer comprising carboxylic acid groups; the method comprising:

- preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in aqueous ammonia; and
- oxidatively polymerising the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group.

The polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group may be any aromatic ring bearing —NH_2 and —COOH moieties in any position, with or without other substituents. In certain preferred embodiments, the substance being polymerised is selected from 2-aminobenzoic acid, 3-aminobenzoic acid or 4-aminobenzoic acid.

Monomers other than amino benzoic acids can be used, for example aniline or pyrrole, or derivatives thereof may be used.

In one aspect, the invention provides a method of preparing a polyaniline copolymer comprising at least one carboxylic acid group; the method comprising:

- preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in aqueous methanesulfonic acid and one or more additional polyaniline precursors; and
- oxidatively polymerising the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group and the one or more additional polyaniline precursors.

In one aspect, the invention provides a method of preparing a polyaniline copolymer comprising at least one carboxylic

preparing the solution of the first polyaniline precursor and the one or more additional polyaniline precursors in aqueous ammonia; and

oxidatively polymerising the first polyaniline precursor and the one or more additional polyaniline precursors.

6. The method of claim 1, wherein the first polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group is selected from the group consisting of 2-aminobenzoic acid, 3-aminobenzoic acid, and 4-aminobenzoic acid.

7. The method of claim 1, wherein the one or more additional polyaniline precursors comprises aniline.

8. The method of claim 1, wherein the ratio of the first polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group: the one or more additional polyaniline precursors is from 99:1 to 1:99.

9. The method of claim 1, wherein the first polyaniline precursor and methanesulfonic acid are present in a ratio of 2:1 to 1:2.

10. The method of claim 1, wherein the polymerisation is carried out by APS.

11. The method of claim 1, further including the step of collecting precipitated polyaniline by filtration.

- preparing a solution of a polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group in aqueous ammonia and one or more additional polyaniline precursors; and
- oxidatively polymerising the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group and the one or more additional polyaniline precursors.

The polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group may be any aromatic ring bearing —NH_2 and —COOH moieties in any position, with or without other substituents. In certain preferred embodiments, the substance being polymerised is selected from 2-aminobenzoic acid, 3-aminobenzoic acid or 4-aminobenzoic acid. The one or more additional polyaniline precursors may be any amino substituted aromatic ring, which is in some cases preferably comprises aniline.

Figure 3 shows a possible structure of poly(4-aminobenzoic acid).

Figure US09296861-20160329-C00002

Monomers other than amino benzoic acids can be used, for example aniline and other derivatives thereof or pyrrole and derivatives thereof may be used.

The most preferred copolymers are those formed from mixtures of aniline and 2-aminobenzoic acid, aniline and 3-aminobenzoic acid or aniline and 4-aminobenzoic acid. Figure 4 shows a possible structure of copolymers of aniline and 4-aminobenzoic acid. Y and Z are the numbers of repeat units.

Figure US09296861-20160329-C00003

The ratio of the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group: the one or more additional polyaniline precursors is from 99:1 to 1:99. Alternatively, ratios in the range 72:25 to 25:75 may be used.

If aqueous methane sulfonic acid is used, it is preferably in a concentration of 0.1 to 10 M in water. It is generally preferred if the ratio of concentration of ABA to methanesulfonic acid is from 2:1 to 1:2. For example, it is preferred to use a solution of methanesulfonic acid of around 1 M and an ABA concentration of around 0.5 M.

The polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group is preferably dissolved in the aqueous methane sulfonic acid and oxidising agent is added. If a copolymer is desired, additional polyaniline precursors may be added in a suitable compatible solvent, which may include water or aqueous methane sulfonic acid.

If ammonia is used, the polyaniline precursor having at least one aromatic amine group and at least one carboxylic acid group is suspended in water and ammonia is added to dissolve it. The amount and concentration required can be readily determined. Typically, commercial strength ammonia is added to a suspension of the ABA in water until the monomer is dissolved. The pH is readily maintained at around neutral to slightly alkaline pHs, for example around pH 7-8.

The reaction of aminobenzoic acid and/or aniline to synthesize the homopolymer or copolymer is carried out in an acidic or near neutral medium in the presence of an oxidizing agent. Any suitable oxidizing agent may be used. Suitable oxidizing agents include, although are not limited to ammonium persulphate, potassium ferricyanide, potassium iodate, hydrogen peroxide, cerium (IV) sulphate, potassium dichromate and sodium vanadate. For neutral/alkaline based reaction, preferably the oxidizing agent is ammonium persulphate or hydrogen peroxide.

The methods of the present invention will also usually further include the step of collecting the precipitated poly aminobenzoic acid homopolymer or copolymer by filtration.

DESCRIPTION

Aminobenzoic acids have low solubility in water and in common acids used to carry out oxidative polymerization. For example, 3-ABA has only around 5 wt % solubility in 1 M HCl, which is typical for ABAs generally. Even if the aminobenzoic acids can be dissolved to some extent, it is difficult to get them into solution at sufficiently high concentrations to achieve good yields of the resultant polyaniline polymer or copolymer. The present inventors have developed solvent systems based around methanesulfonic acid or ammonia that enable the monomer to be dissolved in MSA or ammonia at high concentration (15% by weight or higher)

The methods of the present invention enable the practical large scale production of PANIs, particularly those starting from amino benzoic acid derivatives, at room temperature. Because of the good solubility of the starting monomers, the reaction yield and starting monomer consumption is high and the reaction time is reduced, resulting in a less wasteful and more economic synthesis. Moreover, the products of the present invention have been found to have high molecular weight and, where copolymers are concerned, high incorporation of n-ABA in the resultant copolymer is observed.

Try the new Google Patents, with machine-classified Google Scholar results, and Japanese and South Korean patents.

Oxidative polymerisation of 3-amino benzoic acid to the corresponding polycarboxylated PANI was carried out under standard conditions using 1M HCl as monomer solvent and APS as oxidant.

From 150 ml 1 M HCl solution containing 2.2 g (16 mmol) 3-ABA, 0.0154 g polymer was obtained (0.7% yield*) when the reaction was performed at 10° C. for 7 days

From 200 g 1 M HCl solution containing 10 g n-ABA monomer, 1 g polymer was obtained (10% yield*), when the reaction was performed at room temperature for 48 h *Yield:=100×[mass of the polymer]/[mass of the (co)monomer(s)]

INVENTIVE EXAMPLES

Methane Sulphonic Acid as Solvent

Poly(n-amino benzoic acid) homopolymers, where n=2, 3 or 4 (P(n-ABA)) and poly(n-amino benzoic acid-co-aniline) copolymers (P(n-ABA-co-Ani)) were synthesised in 1 M methane sulfonic acid (MSA) at 25° C. (ambient temperature), with ammonium persulfate (APS) as the oxidizing agent. The monomer(s) concentration and the mole ratio of monomer(s) to APS were kept constant at 0.5 M and 1:1.25 respectively. The mole ratio of n-aminobenzoic acid (n-ABA) to aniline (Ani) in the comonomer mixtures was varied from 99:1 to 1:99, or more usually 75:25 to 25:75.

The maximum concentration of n-aminobenzoic acid (n-ABA) in 1 M MSA is about 15%, which may be higher in more concentrated MSA.

Homopolymers

Homopolymers of the present invention can be designated as follows:

- HpMn: Hp=Homopolymer, M=methane sulfonic acid (MSA), n=position of —COOH functional group (4 or 3 or 2) in n-ABA precursor.
- HpAn: Hp=Homopolymer, A=ammonia, n=position of —COOH functional group (4 or 3 or 2) in n-ABA precursor.

Synthesis of PANI homopolymers of aminobenzoic acids P(n-ABA): 13.86 g of 4-ABA was dissolved in 100 mL of 1 M MSA. 28.52 g of APS was dissolved in 100 mL of water and added dropwise to the monomer solution with constant stirring. Polymerisation was continued with stirring for 24 h. The polymeric product that precipitated from the solution was collected by filtration, washed thoroughly with distilled water then (vacuum) dried at 50° C. From this process 7.2 g polymer HpM4 was obtained (52% yield).

The yield can be seen to be significantly better than that obtained from the use of HCl as solvent.

The use of 3-ABA and 2-ABA in an identical manner resulted in the synthesis of a homopolymer of 3-aminobenzoic HpM3 and a homopolymer of 2-aminobenzoic acid HpM2 respectively.

Table 1 shows the properties of HpMn homopolymers synthesised using MSA as solvent. The yields are significantly better than using traditional solvents, such as HCl.

TABLE 1

Antimicrobial property (Minimum inhibitory concentration) (μmol DPPH %		Free radical scavenging scavenged/mg	Conductivity				
Material	Monomer	Colour	Yield (%)	Mol wt. (g/mol)	Gram +ve (<i>S. aureus</i>)	Gram -ve (<i>E. coli</i>)	(S/cm)
HpM4	4ABA	Dark brown	52	19826	0.5	1	64
HpM3	3ABA	Dark brown	18	12947	1	>2%	60
HpM2	2ABA	Dark brown	30	22200	0.25	1	61

Copolymers of the present invention can be designated as follows:

- CpMnYZ: Cp=Copolymer, M=methane sulfonic acid (MSA), n=position of —COOH functional group (4 or 3 or 2) in n-ABA precursor, YZ ratio Y:Z of n-ABA:aniline in feed.
- CpAnYZ: Cp=Copolymer, A=ammonia, n=position of —COOH functional group (4 or 3 or 2) in n-ABA precursor, YZ ratio Y:Z of n-ABA:aniline in feed.

Synthesis of copolymers of aminobenzoic acids and aniline P(n-ABA-co-Ani): For a typical synthesis of P(n-ABA-co-Ani) (starting from a solution with equimolar proportions of comonomers, for example), 6.94 g of n-ABA was dissolved in 100 mL of 1 M MSA. 4.66 g aniline was added to this solution and stirred for 15 mins. 28.52 g of APS was dissolved in 100 mL of water and added dropwise to the solution of the monomers with constant stirring. Polymerisation was continued with stirring for 24 h. The polymer product that precipitated from the solution was collected by filtration, washed thoroughly with distilled water then (vacuum) dried at 50° C.

Oxidative synthesis of copolymer CpM411: 6.94 g of 4-ABA was dissolved in 100 mL of 1 M MSA. 4.66 g aniline was added to this solution and stirred for 15 mins. 28.52 g of APS was dissolved in 100 mL of water and added dropwise to the solution of the monomers with constant stirring. Polymerisation was continued with stirring for 24 h. The polymer product that precipitated from the solution was collected by filtration, washed thoroughly with distilled water then (vacuum) dried at 50° C. From this process 11.6 g copolymer (CpM411) was obtained (100% yield).

Under similar conditions, copolymers of 4-ABA and aniline, copolymers of 3-ABA and aniline, copolymers of 2-ABA and aniline at various monomer feed ratio (from 99:1 to 1:99) can be synthesized.

Table 2 shows the properties of copolymers (CpMnYZ) synthesised in acidic medium.

TABLE 2

Antimicrobial property (Minimum inhibitory concentration) % of DPPH		Free radical scavenging (micromoles of sample) %					Conductivity (S/cm)
Material	Monomer ratio (n-ABA:Aniline)	Colour	Yield (%)	Gram +ve (<i>S. aureus</i>)	Gram -ve (<i>E. coli</i>)	scavenged/mg	
CpM431	4ABA:Aniline (3:1)	Dark brown	78	0.25	2	57	<10 ⁻⁵
CpM411	4ABA:Aniline (1:1)	Dark brown	100	0.5	>2	59	0.002
CpM413	4ABA:Aniline (1:3)	Dark green	112	0.5	>2	60	1
CpM331	3ABA:Aniline (3:1)	Dark brown	85	0.5	2	57	<10 ⁻⁵
CpM311	3ABA:Aniline (1:1)	Dark brown	101	2	>2	54	0.002
CpM313	3ABA:Aniline (1:3)	Dark green	114	>2	>2	46	0.6
CpM231	2ABA:Aniline (3:1)	Dark brown	78	0.5	2	54	<10 ⁻⁵
CpM211	2ABA:Aniline (1:1)	Dark brown	81	0.5	>2	47	0.04
CpM213	2ABA:Aniline (1:3)	Dark green	121	0.5	>2	54	2

Ammonia as Solvent
Homopolymers

Synthesis of HpA4 in non-acidic medium (by neutralizing monomer with ammonia): 13.86 g monomer (4-ABA) was

The polymeric product that precipitated out from the solution was collected by filtration, washed thoroughly with distilled water then (vacuum) dried at 50° C. From this process 11.37 g polymer HpA4 was obtained (82% yield).

Again, the yield can be seen to be significantly better than that obtained from the use of HCl as solvent. Under the same conditions HpA3 and HpA2 can be synthesized in non-acidic medium (by neutralizing monomer with ammonia.)

Figure 5 below shows a possible reaction scheme for synthesis of poly(4-aminobenzoic acid).

Figure US09296861-20160329-C00004

Table 3 shows the properties of HpAn homopolymers synthesised by pre-neutralization with ammonia

TABLE 3

Material	Monomer	Colour	Yield (%)	Mol wt (g/mol)	Gram +ve (S. aureus)	Gram -ve (E. coli)	sample %	Conductivity (S/cm)
HPA4	4ABA	Dark brown	82	18362	0.125	>2	55	<10 ⁻⁵
HPA3	3ABA	Dark brown	82	62847	1	2	61	<10 ⁻⁵
HPA2	2ABA	Dark brown	71	44645	0.5	1	56	<10 ⁻⁵

Copolymers

Oxidative synthesis of copolymer CpA411: 6.94 g monomer (4-ABA) was dissolved in 100 mL water by neutralizing with 4 mL of 28% ammonia. 4.66 g aniline was added to this solution and stirred for 15 mins. 28.52 g of APS was dissolved in 96 mL of water and added dropwise to the monomer solution with constant stirring. Polymerisation was continued with stirring for 24 h. The polymeric product that precipitated out from the solution was collected by filtration, washed thoroughly with distilled water then (vacuum) dried at 50° C. From this process 10.2 g copolymer (CpA411) was obtained (88% yield).

Under similar conditions, copolymers of (4-ABA) and aniline, (3-ABA) and aniline, and (2-ABA) and aniline at various monomer feed ratio (can be from 99:1 to 1:99) can be synthesized in acidic medium.

Table 4 shows a property chart of copolymers (CpAnYZ) synthesised by pre-neutralization of monomer n-ABA with ammonia.

TABLE 4

Material	Monomer ratio (n-ABA:Aniline)	Colour	Yield (%)	Gram +ve (S. aureus).	Gram -ve (E. coli)	scavenged/mg of sample %	Conductivity (S/cm)
CpA431	4ABA:Aniline (3:1)	Dark brown	83	0.06%	>2%	60	<10 ⁻⁵
CpA411	4ABA:Aniline	Dark	88	0.13%	>2%	58	<10 ⁻⁵

Try the new Google Patents, with machine-classified Google Scholar results, and Japanese and South Korean patents.

TABLE 4

CpA413 4ABA:Aniline (1:3)	Dark green	90	0.25%	>2%	55	0.0003
CpA331 3ABA:Aniline (3:1)	Dark brown	83	0.125	>2	58	<10 ⁻⁵
CpA311 3ABA:Aniline (1:1)	Dark brown	87	0.125	>2	61	<10 ⁻⁵
CpA313 3ABA:Aniline (1:3)	Dark green	85	0.25	>2	55	0.00005
CpA231 2ABA:Aniline (3:1)	Dark brown	72	0.125	1	53	<10 ⁻⁵
CpA211 2ABA:Aniline (1:1)	Dark brown	91	0.125	2	52	<10 ⁻⁵
CpA213 2ABA:Aniline (1:3)	Dark green	93	0.25	>2	56	<10 ⁻⁵

PATENT CITATIONS

Cited Patent	Filing date	Publication date	Applicant	Title
US5932144	Aug 22, 1997	Aug 3, 1999	Mitsubishi Rayon Co., Ltd.	Soluble aniline conducting polymers
US6136909 *	Jun 17, 1999	Oct 24, 2000	Industrial Technology Research Institute	Preparation of conductive polymeric nanocomposite
US7374703	Jun 28, 2005	May 20, 2008	The Ohio State University	Synthesis of nanofibers of polyaniline and substituted derivatives
US20040110051 *	May 23, 2003	Jun 10, 2004	Bollepalli Srinivas	Sulfonated conducting polymer-grafted carbon material for fuel cell applications
WO2009041837A1	Sep 26, 2008	Apr 2, 2009	Auckland Uniservices Limited	Bioactive aniline copolymers

* Cited by examiner

NON-PATENT CITATIONS

Reference	
1	International Search Report prepared by the Australian Patent Office on Jun. 15, 2012, for International Application No. PCT/NZ2012/000047.
2	Yan H., et al. "Novel Syntheses of poly(o-aminobenzoic acid) and copolymers of o-aminobenzoic acid and aniline as potential candidates for precursors of polyaniline." Bull.Chem.Soc.Jpn., (1996) vol. 69, pp. 2395-2401.

CLASSIFICATIONS

International Classification	H05K3/10 , H01B1/02 , C08G73/06 , C08G73/02 , C08J7/04
Cooperative Classification	H01B1/026 , C08J2379/02 , C08G73/0611 , H05K3/105 , C08J7/04 , C08G73/0266

LEGAL EVENTS

Date	Code	Event	Description
Oct 4, 2013	AS	Assignment	Owner name: AUCKLAND UNISERVICES LIMITED, NEW ZEALAND Free format text: ASSIGNMENT OF ASSIGNORS INTEREST;ASSIGNORS:RAY, SUDIP;EASTEAL, ALLAN JAMES;REEL/FRAME:031351/0489 Effective date: 20120418

[Google Home](#) - [Sitemap](#) - [USPTO Bulk Downloads](#) - [Privacy Policy](#) - [Terms of Service](#) - [About Google Patents](#) - [Send Feedback](#)

Data provided by IFI CLAIMS Patent Services